



Product name	:	MoTip Zinc spray	
Article number	:	04061	
Supplier / Producer	:	MOTIP DUPLI B.V.	
		Wolframweg 2	
		NL-8471 XC WOLVEGA	
		Telephone number	+31 561 – 69 44 00
		Telefax number	+31 561 – 69 44 31

Product description

High quality zinc spray to treat galvanised and untreated steel.

Product characteristics

Fast drying
Good filling property
Outstanding cathodic corrosion prevention
Resistant to petrol, chemicals and weather influences
Spot-weldable
Excellent adhesion

Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Epoxy-ester
Colour	:	Grey
VOC-content	:	Approximately 54% w/w
Solid content	:	Approximately 46% w/w
Coverage	:	1,25 to 1,75 m ²
Dust dry	:	After 10 to 15 minutes
Tack free	:	After 20 to 30 minutes
Hardened/re-sprayable	:	After 24 hours
Heat resistant	:	To 350°C

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the zinc spray in several thin layers. Before applying the next layer, again shake the aerosol. When desired, after drying a primer and a lacquer can be applied.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.