



<b>Product name</b>	:	<b>MoTip Kompakt Clear Lacquer, high gloss</b>
<b>Article number</b>	:	<b>50000</b>
<b>Supplier / Producer</b>	:	<b>MOTIP DUPLI B.V.</b>
		<b>Wolframweg 2</b>
		<b>NL-8471 XC WOLVEGA</b>
		<b>Telephone number</b> +31 561 – 69 44 00
		<b>Telefax number</b> +31 561 – 69 44 31

---

## Product description

High quality finish to create a high-gloss preservative for all car repair lacquers.

## Product characteristics

Fast drying  
Excellent filling property  
Excellent flow  
Lasting gloss  
Scratch free and shock proof  
Resistant to weather influences  
UV resistant and non-fading  
Excellent adhesion

## Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Acrylic resin
VOC-content	:	Approximately 90% w/w
Solid content	:	Approximately 10% w/w
Gloss	:	High gloss 90 at an angle of 60°
Coverage	:	1,25 to 1,75 m <sup>2</sup>
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 2 hours
Heat resistant	:	To 110°C

## Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

### Pre Treatment

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).

### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the clear lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**