





Q 70-277


XTRM-DRY Clearcoat


Characteristics


70-277 HS clear coat with a very short drying time. XTRM-DRY is a clear coat with a very high dry matter content (High Solid). The resulting coat has high gloss, depth, and the clear coat does not flow down. It is designed for painting small and large surfaces of vehicles, machinery and equipment. The clear coat is characterized by high resistance to scratching.

Physical Characteristics


 

 24 month


 2004/42/IIB(d)(420)<420

 70-277 :100
70-277HN :50

Application


 16 - 20 s
4 mm DIN

 1,1 - 1,4 mm
4 bar

 HVLP 1,1 - 1,4 mm
2 bar

 2

 5 min.

 40 - 70 µm

Drying

 20°C

 40°C

 60°C

 5 min

 20°
30 min



dust free: 15 min
set to touch: 25 min
through dry: 1 h

ready for assembly 15 min

ready for assembly 5 min

Storage



Store the product in a ventilated place. Keep away from direct exposure to sunlight. Keep between +5°C and 20°C.

Safety



For more informations check the safety data sheet.



This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products. Copyright: Q-Company Int. GmbH, all rights reserved.