

Product Description

Water-based white pigmented lacquer for the treatment of inner lists and panels of light wood

Directions for use

Surface must be clean firm and sustainable.

Wood moisture should not exceed 20% RH

Any resin exudations to be removed and be after dried with appropriate thinner.

The product is thoroughly stirred prior to use.

Optionally diluted with water to spraying viscosity.

Lye 1718 requires 2 x application for proper staining and optimal prevention of yellowing of the timber.

Cleaning instructions

Clean with water immediately after use. Once a week clean the equipment using an appropriate cleaning agent.

Safety & environment

Personal protection equipment must be used. For information regarding safety, health and environment see Material Safety Data Sheet (MSDS) at www.bj.dk.

Sprayguide

Spraying	Nozzle	Air pressure	Ass. Air	Filter
Airless with Finefinish	10-14 (graco)			100 mesh

Technical data

Binder: Acrylic

Type:

Gloss: Approx. 10, semi matt

Vol. dry: Approx. 16%

Colours: Lye 1718

Drying: Approx. 1 hour, recoatable after approx. 4 hours at 20 °C, 65% RF.

Application: Optimum temperature for the product, subject and location: 18-22 °C and R/F approx. 50%

Thinning: Water. Normally not to be diluted

Coverage: 10-15 m² / liter depending on the absorbency of the wood and application method

Tools: Applicator/painting machine or spray

Mal-Code: